The Serbian Society for Ceramic Materials
The Academy of Engineering Sciences of Serbia
Institute for Multidisciplinary Research - University of Belgrade
Institute of Physics - University of Belgrade
Vinča Institute of Nuclear Sciences - University of Belgrade




Edited by:
Branko Matović
Zorica Branković
Dušan Bućevac
Vladimir V. Srdić

Programme and Book of Abstracts of The Third Conference of The Serbian Society for Ceramic Materilas **publishes abstracts from the field of ceramics, which are presented at international Conference.**

***Editors-in-Chief***
Dr Branko Matović
Dr. Zorica Branković
Dr. Dušan Bučevac
Prof. Vladimir V. Srdić

***Publisher***
Institute for Multidisciplinary Research, University of Belgrade
Kneza Višeslava 1, 11000 Belgrade, Serbia

***For Publisher***
Prof. Dr Sonja Veljović Jovanović

***Printing layout***
Vladimir V. Srdić

***Press***
Zonex, Beograd, Serbia

CIP – Каталогизација у публикацији
Народна библиотека Србије, Београд

666.3/.7(048)
66.017/.018(048)

DRUŠTVO za keramičke materijale Srbije. Konferencija (3 ; 2015 ; Beograd)

Programme ; and the Book of Abstracts / 3rd Conference of the Serbian Society for Ceramic Materials, 3CSCS-2015, June 15-17, 2015, Belgrade, Serbia ; [organizers] The Serbian Society for Ceramic Materials... [et al.] ; edited by Branko Matović ... [et al.]. - Belgrade : Institute for Multidisciplinary Research, University, 2015 (Beograd : Zonex). - 128 str. ; 24 cm

Tiraž 140. - Str. 6: Welcome Message / Branko Matovic. - Registar.

ISBN 978-86-80109-19-0

a) Керамика - Апстракти b) Наука о материјалима - Апстракти c) Наноматеријали - Апстракти

COBISS.SR-ID 215704332

**The Serbian Society for Ceramic Materials**
**The Academy of Engineering Sciences of Serbia**
**Institute for Multidisciplinary Research-University of Belgrade**
**Institute of Physics-University of Belgrade**
**Vinča Institute of Nuclear Sciences-University of Belgrade**

# PROGRAMME AND THE BOOK OF ABSTRACTS

## 3rd Conference of The Serbian Society for Ceramic Materials

**June 15-17, 2015**
**Belgrade, Serbia**
**3CSCS-2015**

Edited by:
**Branko Matović**
**Zorica Branković**
**Dušan Bućevac**
**Vladimir V. Srdić**

## SPECIAL THANKS TO









Braća Rajković


detall
Opremanje enterijera, nameštaj po meri


Š.U.N.D.


DVA JELENA
THE TWO DEER RESTAURANT


Holiday Inn
Express


Belgrade • City


Turistička
organizacija
Beograda


SERBIA


NATIONAL TOURISM
ORGANISATION of
SERBIA

# Committees

## Organizer

- The Serbian Society for Ceramic Materials
- The Academy of Engineering Sciences of Serbia
- Institute for Multidisciplinary Research-University of Belgrade
- Institute of Physics-University of Belgrade
- Vinča Institute of Nuclear Sciences-University of Belgrade

## Scientiific Committee

1. Dr. Slavko Bernik, *Institute "Jožef Štefan", Ljubljana, Slovenia*
2. Prof. Dr. Chang-An Wang, *School of Materials Science and Engineering, Tsinghua University, P. R. China*
3. Prof. Dr. Claus Rebholz, *University of Cyprus, Cyprus*
4. Dr. Ravi Kumar, *Indian Institute of Technology-Madras (IIT Madras), India*
5. Katsumi Yoshida, *Tokyo Institute of Technology, Japan*
6. Elisabetta Di Bartolomeo, *Dept. of Chemical Science and Technologies, University of Rome Tor Vergata, Italy*
7. Prof. Dr. Lidija Ćurković, *Faculty of Mechanical Engineering and Naval Architecture, University of Zagreb, Croatia*
8. Dr. Snežana Bosković, *Institute of Nuclear Sciences Vinca, University of Belgrade, Serbia*
9. Prof. Dr. Biljana Stojanović, *Institute for Multidisciplinary Research - University of Belgrade, Serbia*
10. Prof. Dr. Vladimir V. Srdić, *Faculty of Technology, University of Novi Sad, Serbia*
11. Dr. Zorica Branković, I*nstitute for Multidisciplinary Research - University of Belgrade, Serbia*
12. Dr. Goran Branković, *Institute for Multidisciplinary Research - University of Belgrade, Serbia*
13. Dr. Zorana Dohčević-Mitrović, *Institute of Physics, University of Belgrade, Serbia*
14. Dr. Branko Matović, *Institute of Nuclear Sciences Vinca, University of Belgrade, Serbia*
15. Dr. Aleksandra Zarubica, *University of Nis, Serbia*

16. Prof. Dr. Tatjana Volkov-Husović, *Faculty of Technology and Metallurgy, University of Belgrade, Serbia*
17. Dr. Miroslav Komljenović, *Institute for Multidisciplinary Research-University of Belgrade, Serbia*
18. Dr. Maja Sćepanović, *Institute of Physics, University of Belgrade, Serbia*
19. Dr. Tatjana Srećković, *Institute for Multidisciplinary Research - University of Belgrade, Serbia*
20. Dr. Dejan Zagorac, *INN Vinca, University of Belgrade, Serbia*

## Organizing Committee

1. Dr. Bratislav Todorović, *Faculty of Technology, Leskovac, Serbia*
2. Dr. Mirjana Cocić, *Technical Faculty, Bor, Serbia*
3. Dr. Mirjana Grujić-Brojčin, *Institute of Physics, Zemun, Serbia*
4. Prof. Radmila Jančić-Heinemann, *Faculty of Technology and Metallurgy, University of, Belgrade, Serbia*
5. Dr Marija Milanović, *Faculty of Technology, University of Novi Sad, Serbia*
6. Dr. Zorica Marinković-Stanojević, *Institute for Multidisciplinary Research, Belgrade, Serbia*
7. Dr. Sanja Martinović, *IHTM Belgrade, Serbia*
8. Dr. Marija Prekajski, *Institute of Nuclear Sciences "Vinča", Belgrade, Serbia*
9. Dr. Marijan Randjelović, *PMF, University of Niš, Serbia*
10. Dr. Ivan Stjepović, *Faculty of Technology, University of Novi Sad, Serbia*
11. Dr. Mirjana Vijatović-Petrović, *Institute for Multidisciplinary Research, Belgrade, Serbia*
12. Dr. Milica Vlahović, *IHTM Belgrade, Serbia*
13. Dr. Jelena Purenovic, *Faculty of Technical Science, Cacak, Serbia*
14. Dr. Aleksandar Savić, *Institute for Multidisciplinary Research, Belgrade, Serbia*

P-41

## ELECTRONIC PROPERTIES OF PSEUDOBROOKITE NANOSTRUCTURED THICK FILMS

Miloljub D. Lukovic[1], Zorka Z. Vasiljevic[2], Obrad S. Aleksic[1], Maria V. Nikolic[1], Nikola Tasic[1]

*[1]Institute for Multidisciplinary Research, University of Belgrade, Serbia*
*[2]Institute of Technical Sciences of SASA, Belgrade, Serbia*

Thick film pastes were formed using $TiO_2$ (anatase) and $Fe_2O_3$ (hematite) nanopowder in different weight ratios, organic vehicle and glass fritt. Two types of test matrices (sandwich and interdigitated) were screen printed on alumina substrate using conductive PdAg paste and sintered at 850$^o$C/10 minutes in a conveyor furnace. The sandwich thickness and interdigitated electrode spacing were varied. UI characteristics were measured enabling determination of the voltage threshold typical for oxide semiconductors. Measurements of DC resistance vs. temperature enabled determination of the exponential factor B from NTC behavior.

P-42

## MAGNETIC PROPERTIES OF NICKEL MANGANITE OBTAINED BY A COMPLEX POLYMERIZATION METHOD

Slavica M. Savić[1], Marin Tadić[2], Zvonko Jagličić[3], Lidija Mančić[4], Katarina Vojisavljević[1], Goran Branković[1]

*Institute for Multidisciplinary research, University of Belgrade, Kneza Viseslava 1, 11000 Belgrade, Serbia*
*Condensed Matter Physics Laboratory, Vinca Institute, University of Belgrade, POB 522, 11000 Belgrade, Serbia*
*University of Ljubljana, Faculty of Civil Engineering and Geodesy, Institute of Mathematics, Physics and Mechanics, Jadranska 19, 1000 Ljubljana, Slovenia*
*[4]Institute of Technical Sciences SASA, Knez Mihailova 35/IV, 11000 Belgrade, Serbia*

Spinel materials based on Mn and Ni has been intensively studied over the past years due to their excellent semiconductor properties. Nickel manganite as NTC thermistor is widely used today in different industrial sectors. Here we report the complex polymerization method (CPM) for producing nickel manganite fine particles with a homogeneous distribution of constituent cations in the crystal lattice

that ensures formation of dense monophased ceramic with the novel magnetic properties after been sintered in oxygen and air atmosphere. Phase composition of the synthesized materials was examined by XRPD, while the morphology of the powder and microstructure of ceramic were investigated using FESEM and SEM analyses, respectively. The magnetic properties of the samples have been studied by measuring the temperature and field dependence of magnetization.

Magnetic measurements of M(T) reveal rather complex magnetic properties and multiple magnetic phase transitions. In the case of air atmosphere we found three magnetic phase transitions with transition temperatures at $T_{M1}$=35 K, $T_{M2}$=101 K and $T_{M3}$=120 K. $T_{M1}$ maximum is strongly dependent on the strength of the applied magnetic field ($T_{M1}$ decreases with increasing applied field) whereas the $T_{M3}$ is field independent The values of the coercivity, remanent magnetization and saturation magnetization at 100 K are: $H_C$ = 184 Oe, Mr = 1.92 emu/g and $M_S$ = 7.88 emu/g, respectively. The measured values at 5 K are $H_C$ = 1035 Oe, Mr = 7.70 emu/g and $M_S$ = 14.47 emu/g. Moreover, hysteresis properties measured after cooling of the sample in magnetic field show exchange bias effect with an exchange bias field $|H_{EB}|$=196 Oe.

For the sample synthetized in oxygen atmosphere, the magnetization dependence of temperature M(T) and AC susceptibility data obtained from SQUID measurements clearly demonstrates that quadruple magnetic phase transitions can be readily detected at $T_{M1}$~115 K, $T_{M2}$~105 K, $T_{M3}$~38 K and $T_{M4}$~7 K. These findings suggest the novel magnetic transition for nickel manganite at low temperature $T_{M4}$. The temperatures of observed maximums in $\chi$'(T) and $\chi$''(T) parts of susceptibility are frequency independent, whereas the height of the peaks decreases with increasing frequency. The fact that $T_{M4}$ does not shift with the increase of the frequency led us to the conclusion that there are no spin-glass/surface effect and/or blocking temperature/finite size effect connected to the $NiMn_2O_4$ ceramic. Therefore, the low-temperature peak $T_{M4}$ in AC susceptibility is associated with ferromagnetic-like and antiferromagnetic-like magnetic transition in the interfacial FM/AFM internal structure. The exchange bias effect was found in a field cooled hysteresis loops at 5 K. The field cooling of the sample was under a magnetic field of 100 Oe and 10 kOe whereas the determined exchange bias fields were $|H_{EB}|$=129 Oe and 182 Oe, respectively. The analysis of the results and comparison with literature data allowed us to conjecture that the mixed oxidation states of Mn ions and ferromagnetic and antiferromagnetic sublattice orders tailor these interesting magnetic properties.